

Application No.: 10/060,690

Case No.: 56311US007

Amendments to the Claims

This listing of claims will replace all prior versions of claims in the application.

Listing of Claims

1. (currently amended) A composition comprising:
 - (a) a fluoropolymer comprising interpolymerized units derived from a nitrogen-containing cure site monomer;
 - (b) a catalyst composition that includes a compound having the general formula:
$$\{RA\}^{(+)}\{QR'_k\}^{(+)}\{R(A)_n\}^{(-n)}\{OR'_k\}^{(+)}$$
 or the precursors thereof added separately or as a mixture;
wherein R is a C₁-C₂₀ alkyl or alkenyl, C₃-C₂₀ cycloalkyl or cycloalkenyl, or C₆-C₂₀ aryl or aralkyl, which may be nonfluorinated, partially fluorinated, or perfluorinated, [[A]] {R(A)_n}⁽⁻ⁿ⁾ is an acid anion or an acid derivative anion, n is the number of A groups in the anion, Q is phosphorous, sulfur, nitrogen, arsenic, or antimony, each R' is, independently, hydrogen or a substituted or unsubstituted C₁-C₂₀ alkyl, aryl, aralkyl, or alkenyl group, provided that when Q is nitrogen and the only fluoropolymer in the composition consists essentially of a terpolymer of tetrafluoroethylene, a perfluorovinylether, and a perfluorovinylether cure site monomer comprising a nitrile group not every R' is H, and k is one greater than the valence of Q; and
optionally (c) an alcohol of the general formula R²-OH, wherein R² is an alkyl group having from 1 to 20 carbon atoms, and wherein R² can be is optionally fluorinated.
2. (original) A composition according to claim 1 wherein A is selected from the group consisting of: COO, O when R is aryl or alkylaryl, SO₃, SO₂, SO₂NH, PO₃, CF₃CF(CF₃)CH₂O, C_nF_{2n+1}CH₂O wherein n is 0 to 100, CH₂OPO₃, (CH₂O)₂PO₂, C₆H₄O, OSO₃, SO₂¹NR', SO₂¹NSO₂R', and SO₂¹CRSO₂R', wherein R' is as defined in claim 1.

Application No.: 10/060,690

Case No.: 56311US007

3. (cancelled)

4. (currently amended) A composition according to claim 1 wherein a precursor of R(A)_n [[RA]] has the general formula selected from the group consisting of RCOOM, ROSO₃M, RSO₃M, and ROM, wherein M is hydrogen, or an alkali or alkaline earth metal.

5. (currently amended) A composition according to claim 1 wherein R(A)_n [[RA]] is selected from the formula R_x-Ph_y-{(CH₂)_n-D}_m(R")_x-Ph_y-{(CH₂)_n-D}_m wherein each [R_x] R" is the same or different C₁-C₁₀ C₁-C₁₀ alkenyl or alkyl, x is 0 to 5, y is 0 or 1, n is 0 to 10, m is 1 to 5, and D is selected from COO, OSO₃, SO₃, and O (when y is 1), provided that the sum of x and m is 6 or less and provided that x and y are not both zero; RCOO wherein R is alkenyl, an alkyl of 1 to 10 carbon atoms, or an aryl of 6 to 20 carbon atoms; ^HOOC-(CX₂)_p-COO⁽⁻⁾ ⁽⁻⁾OOC-(CX₂)_t-COO⁽⁻⁾ wherein [n], t is 0 to 10, X = H, F, or Cl; and Ph-((CH₂)_p-COO⁽⁻⁾)_q wherein p and q are independently 1 to 4; CF₃CF(CF₃)CH₂O or C_aF_{2a+1}CH₂O C_dF_{2d+1}CH₂O wherein d is 0 to 100; and blends of two or more such compounds.

6. (currently amended) A composition according to claim 1 wherein R(A)_n [[RA]] is selected from the general formula ⁽⁻⁾O_z-Ph-G_y-Ph-O_z⁽⁻⁾ wherein G is a bond or a difunctional aliphatic, cycloaliphatic, or C₁-C₁₃ aromatic radical, or a thio, oxy, carbonyl, sulfinyl, or sulfonyl radical, G and/or Ph are optionally substituted with at least one Cl or F atom, y is 0 or 1, each z is, independently, 1 or 2, and any aromatic ring of the polyoxy compound is optionally substituted with at least one atom of Cl, F, or Br atom, or carboxyl, or an acyl radical, or an alkyl radical; and blends of two or more such compounds.

7. (currently amended) A composition according to claim 1 wherein R(A)_n [[RA]] is selected from the general formula ⁽⁻⁾O-Ph-C(CX₃)₂-Ph-O⁽⁻⁾, wherein X is H, Cl, or F; and blends of two or more such compounds.

Application No.: 10/060,690

Case No.: 56311US007

8. (currently amended) A composition according to claim 1 wherein a precursor of QR'k is selected from the group consisting of tetramethylphosphoniums, tributylallylphosphoniums, selected from the group consisting of tetramethylphosphoniums, tributylallylphosphoniums, 2-tributylbenzylphosphoniums, dibutyl diphenylphosphoniums, tetrabutylphosphonium, tributyl(2-methoxy) propylphosphoniums, triphenylbenzylphosphoniums, and tetraphenylphosphoniums.

9. (currently amended) A composition according to claim 1 wherein a precursor of QR'k is selected from the group consisting of phenyltrimethylammoniums, tetrapentylammoniums, selected from the group consisting of phenyltrimethylammoniums, tetrapentylammoniums, tetrapropylammoniums, tetrahexylammoniums, tetraheptylammoniums, tetramethylammoniums, tetrabutylammoniums, tributylbenzyl ammoniums, tributylallylammoniums, tetrabenzylammoniums, tetraphenylammoniums, diphenyl diethylamino ammoniums, triphenylbenzylammoniums, 8-benzyl-1,8-diazabicyclo[5.4.0]undec-7-eniums, benzyltris(dimethylamino) phosphoniums, and bis(benzyldiphenyl phosphine)iminiums.

10. (original) A composition of claim 1 wherein the catalyst composition is prepared in situ.

11. (original) A composition according to claim 1 wherein the catalyst composition is prepared from components dissolved in a solvent.

12. (original) A composition according to claim 1 wherein the fluoropolymer comprises interpolymerized units derived from (i) tetrafluoroethylene, and optionally (ii) one or more perfluorovinyl ethers of the formula: $\text{CF}_2=\text{CFO}(\text{R}^2_f\text{O})_a(\text{R}^3_f\text{O})_b\text{R}^4_f$ wherein R^2_f and R^3_f are the same or are different linear or branched perfluoroalkylene groups of 1-6 carbon atoms; a and b are, independently, 0 or an integer from 1 to 10; and R^4_f is a perfluoroalkyl group of 1-6 carbon atoms.

Application No.: 10/060,690

Case No.: 56311US007

13. (original) A composition according to claim 12 wherein the fluoropolymer further comprises interpolymerized units derived from monomers selected from the group consisting of perfluoroolefins, partially-fluorinated olefins, non-fluorinated olefins, vinylidene fluoride, and combinations thereof.

14. (original) A composition according to claim 1 wherein said cure site monomer is selected from a fluorinated olefin and a nitrile-containing monomer.

15. (original) A composition according to claim 1 wherein said cure site monomer is a nitrile-containing monomer having the formula $\text{CF}_2=\text{CFO}(\text{CF}_2)_L\text{CN}$; $\text{CF}_2=\text{CFO}(\text{CF}_2)_u\text{OCF}(\text{CF}_3)\text{CN}$; $\text{CF}_2=\text{CFO}[\text{CF}_2\text{CF}(\text{CF}_3)\text{O}]_q(\text{CF}_2\text{O})_y\text{CF}(\text{CF}_3)\text{CN}$; or $\text{CF}_2=\text{CF}[\text{OCF}_2\text{CF}(\text{CF}_3)]_r\text{O}(\text{CF}_2)_t\text{CN}$; wherein L = 2-12; q = 0-4; r = 1-2; y = 0-6; t = 1-4, and u = 2-6; and perfluoro(8-cyano-5-methyl-3,6-dioxa-1-octene).

16. (original) A composition according to claim 1 further comprising a filler selected from fluoropolymer filler, carbon black, and combinations thereof.

17. (original) The composition of claim 1 wherein the fluoropolymer is selected from a fluoroelastomer and a fluoroplastic.

18. (original) The composition of claim 1 wherein the composition has an induction time below about 15 minutes at a temperature of about 175°C.

19. (original) The composition of claim 1 wherein the composition has a scorch resistance greater than the scorch resistance of a comparative composition tested at the same temperature, which comparative composition has the same fluoropolymer composition of claim 1 but with a urotropin curative.

Application No.: 10/060,690

Case No.: 563111US007

20. (withdrawn) The composition of claim 1 further comprising an additional curative material.
21. (withdrawn) The composition of claim 20 wherein the additional curative material is selected from ammonia-generating compounds, substituted triazine derivatives, unsubstituted triazine derivatives, peroxides, bis-aminophenols, bis-amidooximes, and organotin compounds.
22. (original) A shaped article comprising the fluoropolymer composition of claim 1.
23. (withdrawn) The composition of claim 1 further comprising a fluoropolymer containing interpolymerized units derived from monomers selected from the group consisting of perfluoroolefins, partially-fluorinated olefins, non-fluorinated olefins, vinylidene fluoride, perfluorovinyl ethers, and combinations thereof.
24. (withdrawn) The composition according to claim 23 comprising a curative that increases MDR torque in the fluoropolymer composition at 177°C by at least about 0.01 Nm.
25. (withdrawn) The composition of claim 23 further comprising a curative material selected from ammonium salts, ammonia-generating compounds, substituted triazine derivatives, unsubstituted triazine derivatives, peroxides, bis-aminophenols, bis-amidooximes, and organotin compounds; and optionally a coagent.
26. (withdrawn) The composition of claim 25 wherein the coagent is selected from triallyl cyanurate; triallyl isocyanurate; tri(methylallyl) isocyanurate; tris(diallylamine)-*s*-triazine; triallyl phosphite; N,N-diallyl acrylamide; hexaallyl phosphoramide; N,N,N',N'-tetraalkyl tetraphthalamide; N,N,N',N'- tetraallyl malonamide; trivinyl isocyanurate; 2,4,6-trivinyl methyltrisiloxane; and tri(5-norbornene-2-methylene)cyanurate.

Application No.: 10/060,690

Case No.: 56311US007

27. (withdrawn) The composition of claim 25 wherein the additional fluoropolymer includes interpolymerized units containing a halogen that is capable of participation in a peroxide cure reaction and wherein the additional curative is a peroxide, and optionally further comprising a triallyl cyanurate coagent.

28. (withdrawn) A shaped article comprising the fluoropolymer composition of claim 23.

29. (currently amended) The composition of claim 1 wherein R(A)_n [[RA]] is selected from the formula $\text{CF}_3(\text{CF}_2)_n\text{COO}^{(-)}\text{CF}_3(\text{CF}_2)_m\text{COO}^{(-)}$ wherein n is 1, 2, or 6, and wherein QR'_k is selected from tetrabutylphosphonium and tributyl(2-methoxy)propylphosphonium.

30. (currently amended) The composition of claim 1 wherein R(A)_n [[RA]] is selected from the formula $\text{HOOC}(\text{CF}_2)_n\text{COO}^{(-)}\text{OOC}(\text{CF}_2)_p\text{COO}^{(-)}$ wherein [[n]] p is 2 or 4, and wherein QR'_k is selected from tetrabutylphosphonium and tributyl(2-methoxy)propylphosphonium.

31. (currently amended) The composition of claim 1 wherein R(A)_n [[RA]] is selected from acetate and benzoate, and wherein QR'_k is selected from tetrabutylphosphonium and tributyl(2-methoxy)propylphosphonium.

32. (withdrawn) A method of making a fluoropolymer composition comprising the steps of:

a) forming a mixture comprising a fluoropolymer having interpolymerized units derived from a nitrogen-containing cure site monomer, a catalyst composition comprising a compound having the formula: $[\{\text{RA}\}^{(-)}\{\text{QR}'_k\}^{(+)}]\ \{\text{R(A)}_n\}^{(-n)}\{\text{QR}'_k\}^{(+)}$ _n or the precursors thereof added separately or as a mixture, wherein R is a C₁-C₂₀ alkyl or alkenyl, C₃-C₂₀ cycloalkyl or cycloalkenyl, or C₆-C₂₀ aryl or alkylaryl, A is an acid anion or an acid derivative anion group, which may be heterocyclic, Q is P, S, N, As, or Sb, and each R' is, independently, hydrogen or a substituted or unsubstituted C₁-C₂₀ alkyl, aryl, aralkyl, or alkenyl group, provided that when Q is nitrogen and the only fluoropolymer in the composition consists essentially of a

Application No.: 10/060,690

Case No.: 56311US007

terpolymer of TFE, a perfluorovinylether, and a perfluorovinylether cure site monomer comprising a nitrile group not every R' is H, and k is one greater than the valence of Q, and optionally in the presence of an alcohol of the general formula R²-OH, wherein R² is a C₆-C₂₀ alkyl group;

- b) shaping the mixture;
- c) curing the shaped mixture; and optionally
- d) heat aging the cured mixture.

33. (withdrawn) A method according to claim 32 wherein the catalyst is added in a form selected from a compound and a mixture of catalyst precursors.

34. (withdrawn) A method according to claim 32 wherein individual components of the catalyst are separately added to the fluoropolymer composition.

35. (withdrawn) A method according to claim 32 wherein the step of curing further comprises press-curing and optionally post-curing.

36. (cancelled)

37. (withdrawn) A method for increasing the induction period in a curable fluoropolymer composition comprising the steps of:

- a) providing a fluoropolymer comprising interpolymerized units derived from a nitrogen-containing cure site monomer; and
- b) incorporating, into the fluoropolymer, a catalyst composition that includes a compound having the general formula: $[\{RA\}^{(+)}\{QR'_k\}^{(+)}\}] \{R(A)_n\}^{(-n)}\{QR'_k\}^{(+)}_n$ or the precursors thereof added separately or as a mixture, wherein R is a C₁-C₂₀ alkyl or alkenyl, a C₃-C₂₀ cycloalkyl or cycloalkenyl or a C₆-C₂₀ aryl or alkylaryl; A is an acid anion or an acid derivative anion; Q is P, S, N, As, or Sb; each R' is, independently, hydrogen or a substituted or

Application No.: 10/090,690

Case No.: 56311US007

unsubstituted C₁-C₂₀ alkyl, aryl, aralkyl, or alkenyl group, provided that when Q is N and the only fluoropolymer in the composition consists essentially of a terpolymer of TFE, a perfluorovinylether, and a perfluorovinylether cure site monomer comprising a nitrile group not every R' is H; and k is one greater than the valence of Q.

38. (withdrawn) The method of claim 37 further comprising the step of incorporating an alcohol of the general formula R²-OH, wherein R² is a C₁-C₂₀ alkyl group, and wherein R² can be fluorinated.
39. (withdrawn) The method of claim 37 further comprising the step of:
 - c) shaping the composition.
40. (withdrawn) The method of claim [[37]] 39 further comprising the step of:
 - d) curing the shaped composition; and optionally
 - e) heat aging the cured composition.
41. (withdrawn) The method of claim 40 wherein the step of curing includes press-curing, and optionally post-curing.
42. (cancelled)